



www.futrolpetrochem.com

Futrol Petrochem
A chemistry of trust. Since 2001



TECHNICAL DATA SHEET

SPECIFICATION OF TOLUENE DI-ISOCYANATE(TDI)		
PARAMETER	TEST METHOD	UNIT
Appearance	Visual	Clear Liq
Purity (% by wt)	H900.6500S	Min.99.5
Colour (APHA)	H900.1700S	Max .25
Hydrolysable Chlorine (ppm by wt)	H900.3500S	Max .60
Total Acidity (ppm by wt)	H900.0500S	Max.40
Isomer ratio 2,4 TDI (% wt)	H900.4100	80±1
Isomer ratio 2,6 TDI (% wt)	H900.4100	20±1
Sp.gr at 25/4 °C	S690.3000	1.22±0.02
NIC (ppm)	H900.5800	Max.30

For more information about this product and other products in our range please scan the following

WEBSITE
www.futrolpetrochem.com

EMAIL SALES
sales@futrolpetrochem.com