



www.futrolpetrochem.com

Futrol Petrochem

A chemistry of trust. Since 2001



TECHNICAL DATA SHEET

| VIRGIN BASE OIL SN 150 | | | | |
|----------------------------------|-------------|------|---------|------|
| SPECIFICATION | UNIT | MIN. | TYPICAL | MAX |
| Kinematic Viscosity @40°C(cSt) | ASTM D-445 | - | 32 | - |
| Kinematic Viscosity @100°C(cSt) | ASTM D-445 | 4.2 | - | 5.6 |
| Viscosity Index | ASTM D-2270 | - | 100 | - |
| Flash point (COC) °C | ASTM D-92 | 190 | - | 210 |
| Pour point (COC) °C | ASTM D-97 | - | - | -6 |
| Carbon residue (conradson) wt% | ASTM D-189 | - | 0.06 | - |
| Total Acid Number mg KOH/g | ASTM D-664 | - | - | 0.05 |
| Demulsibility | ASTM D-1401 | - | Pass | - |
| Sulfur Content | ASTM D-1552 | 0.15 | - | 0.06 |
| Color | ASTM D-1500 | - | 0.5 | 1 |
| Density %15 °C | ASTM D-4052 | - | 870 | - |
| Copper Corrosion (3hrs @ 100 °C) | ASTM D-130 | - | - | 1A |
| Foam ml | ASTM D-892 | - | Nil | - |

For more information about this product and other products in our range please scan the following

WEBSITE
www.futrolpetrochem.com

EMAIL SALES
sales@futrolpetrochem.com