



www.futrolpetrochem.com

Futrol Petrochem

A chemistry of trust. Since 2001



TECHNICAL DATA SHEET

VIRGIN BASE OIL SN 350				
SPECIFICATION	UNIT	MIN.	TYPICAL	MAX
Kinematic Viscosity @40°C(cSt)	ASTM D-445	-	75	-
Kinematic Viscosity @100°C(cSt)	ASTM D-445	8	-	9.3
Viscosity Index	ASTM D-2270	-	95	-
Flash point (COC) °C	ASTM D-92	220	-	-
Pour point (COC) °C	ASTM D-97	-	-	-6
Carbon residue (conradson) wt%	ASTM D-189	-	0.06	-
Total Acid Number mg KOH/g	ASTM D-664	-	-	0.05
Demulsibility	ASTM D-1401	-	Pass	-
Sulfur Content	ASTM D-1552	0.15	-	0.06
Color	ASTM D-1500	-	2	1
Density %15 °C	ASTM D-4052	-	880	-
Copper Corrosion (3hrs @ 100 °C)	ASTM D-130	-	-	1A
Foam ml	ASTM D-892	-	Nil	-

For more information about this product and other products in our range please scan the following

WEBSITE
www.futrolpetrochem.com

EMAIL SALES
sales@futrolpetrochem.com